

TAZMAN 26 DESIGNER COLORS

Thickness	Hide type	Average size
1.2 – 1.5 mm	European Bovine	4.6 – 5.0 sqmt (48 - 55 sqft)

RESIDENTIAL – CONTRACT – HOSPITALITY - FASHION

TECHNICAL SPECIFICATIONS

Test	Test method	Measurement unit	Result
Tear strenght-Single edge tear	UNI EN ISO 3377-1	N	➤ = 20
Colour fastness to rubbing dry 50 cycles	UNI EN ISO 11640:1998	Grey scale	➤ = 3
Colour fastness to rubbing wet 20 cycles	UNI EN ISO 11640:1998	Grey scale	➤ = 3
Colour fastness to rubbing sweat 20 cycles	UNI EN ISO 11640:1998	Grey scale	➤ = 2
Flexing endurance dry 50.000 cycles	UNI EN ISO 5402		No damage
Colour fastness to artificial light	UNI EN ISO 105 B02 (MET5)	Blue scale	➤ = 2/3
Colour fastness to water spotting – after 30 min.	UNI EN ISO 15 700		Total absorption
Colour fastness to water spotting – after 16 hours	UNI EN ISO 15 700	Grey scale	➤ = 3
Burning behaviour to cigarette and match flame	BS 5852:1979 BS EN 1021-1-2-:2006		Pass

The test results are referred only to the sample tested

THE PRODUCT COMPLIES WITH THE **REACH** REGULATION

LEATHER
MADE IN ITALY