



Nara canvas is available in a choice of weights to provide a durable and lasting product for a variety of applications, from truck tarps and trailer covers, to canopies and swags.

A canvas has to be tough to withstand harsh Australian conditions and application requirements. Nara canvas has been formulated to be just that and more. Nara canvas is water-proofed, mildew resistant and UV stabilised. The poly/cotton blend creates a dimensionally stable product strong enough to cope with these demands and the rigours of more industrial applications.

Property		Method	Units	NARA 10	NARA 12	NARA 16
Composition				Poly/Cotton (75:25)	Poly/Cotton (60:40)	Poly/Cotton (85:15)
Construction				Plain Weave	Plain Weave	Ripstop Weave
Weight			oz/yard <sup>2</sup>	10 ± 5%	15 ± 5%	19.5 ± 5%
			gsm	345 ± 5%	510 ± 5%	660 ± 5%
Width			cm	205	205	205
Tensile Strength	Machine Direction (Ave)	BS 13934-1	lb/2in	≥ 456	≥ 456	≥ 730
			N/5cm	≥ 2000	≥ 2000	≥ 3200
	Cross Direction (Ave)		lb/2in	≥ 205	≥ 251	≥ 616
			N/5cm	≥ 900	≥ 1100	≥ 2700
Tear Strength	Machine Direction (Ave)	BS 13934-1	lb/2in	≥ 9	≥ 12	≥ 34
			N/5cm	≥ 40	≥ 55	≥ 150
	Cross Direction (Ave)		lb/2in	≥ 16	≥ 27	≥ 36
			N/5cm	≥ 70	≥ 120	≥ 160
Water Penetration (Hydrostatic)		SANS 5099	inches	≥ 31	≥ 24	≥ 20
			mm	≥ 800	≥ 600	≥ 500
Water Repellency		AATCC 22	Rating (0-100)	≥ 90	≥ 90	≥ 90
Colour Fastness to UV		ISO 105 B04	Rating (0-8)	≥ 6	≥ 6	≥ 6
Dimensional Stability		ISO 7771	%	< 2%	< 2%	< 2%
Abrasion Resistance (Martindale)		ASTM D4966-98	Cycles	70,000	70,000	70,000